



- Robust and abrasion resistant surface
- Efficient installation with two-way integrated selfadhesive strips and verified system accessories
- Can be exposed to the weather for 4 weeks

Packaging

| Roll width | Roll length | Roll area | Roll weight |
|------------|-------------|-----------|-------------|
| [m] | [m] | [m²] | [kg] |
| 1,5 | 50 | 75 | 13 |

Characteristics

| Material | PP fleece with polymer coating | | | |
|--|--------------------------------|-----|--|--|
| Thickness [mm] | 0,50 | | | |
| Water vapour diffusion equivalent [m] | | | | |
| Water vapour diffusion i | 4000 | | | |
| Mass [g/m²] | 170 | | | |
| Watertightness [kPa] | ≥ 2 | | | |
| Temperature resistance | -40 to +80 | | | |
| Minimum application ter | 0 | | | |
| Reaction to fire (EN 135 | Е | | | |
| Tensile strenght [N/5 cn | n] longitudinal | 230 | | |
| | transversal | 170 | | |
| Elongation at maximum tensile strength [%] | | | | |
| - | Iongitudinal | 50 | | |
| | transversal | 40 | | |
| Resistance to tearing (nail shank) [N] | | | | |
| | longitudinal | 135 | | |
| | transversal | 175 | | |
| | | | | |

CE

Product description

PAVATEX DSB 2 is used as an airtight vapour control on roof sheathing for over-rafter insulation with PAVATEX soft woodfibre boards. The longitudinal joints are sealed with the integrated self-adhesive strips. The transversal joints, the connections and the penetrations are sealed using PAVATEX sealing products.

If mechanically secured, PAVATEX DSB 2 can be left exposed to the weather for 4 weeks.

Always consult the local regulations and installation guidelines of the manufacturer.

Health, Environment and Safety

This product does not contain any substance which is likely to be detrimental to your health or to the environment and complies with generally admitted Health and Safety Requirements.

Storage

Store cool and dry, lying down or upright, protected from sunlight and humidity.

TDS-NE-PROEU0004.a/EN

SOPREMA reserves the right to amend the composition of its material and consequently their prices, without prior notice. For this reason, all orders will be accepted only in accordance with the conditions and technical specifications in force at the date of order.

