



Technical Data

Property	Value		Test method
Temperature range	from -40 °C* to +110 °C		EN 14706 EN 14707
Thermal conductivity λ W/(m·K)	Thicknesses $\leq 25\text{mm}$ -20 °C = 0,031 0 °C = 0,033 +20 °C = 0,035 +40 °C = 0,037	Thicknesses $> 25\text{mm}$ -20 °C = 0,034 0 °C = 0,036 +20 °C = 0,038 +40 °C = 0,040	EN 13787 EN ISO 8497
Corrosion problems	pH neutral (7±0,5)		EN 13468
Permeability μ	≥ 10000	≥ 7000	EN 12086
Ecological data	CFC HCFC free		
Fire	Euroclass B _L -s2, d0		EN 13501-1

* For applications below 0°C please contact our technical department.

The Company reserves the right to change data and technical requirements without notice.